

химичен състав на марки стомани за емайлиране



EN 10209	C	Mn	P	S	Ti
Марка	Max.	Max.	Max.	Max.	Max.
DC01EK	0.09	0.50	0.030	0.050	-
DC04EK	0.08	0.40	0.030	0.050	-
DC03ED	0.004	0.40	0.035	0.050	-
DC04ED	0.004	0.40	0.030	0.050	-
DC06ED	0.004	0.35	0.020	0.050	0.30